

9400 SYSTEM HIGH GLOSS POLYESTER URETHANE LEVELING ADDITIVE

DESCRIPTION AND USES

A specially formulated blend of surfactants which improves the appearance of 9400 System High Gloss Polyester Urethane finishes. Primarily for use when the 9400 System finishes are to be applied by brush or roller. The Leveling Additive may also be used for airless spray application.

The Leveling Additive increases the flow and leveling of the 9400 System finishes, resulting in a smoother, more uniform finish, with no decrease in overall performance. It also helps reduce effervescence and the "orange peel" effect sometimes produced when the finishes are applied by airless spray. Additionally, the appearance of materials applied during difficult periods of hot weather is considerably improved.

PRODUCTS

SKU Description
9404730 8 ounce screw-top cans

APPEARANCE

Thin, clear liquid

PRODUCT APPLICATION

INSTRUCTIONS

Add 8 fluid ounces (½ pint) of 9404 per gallon of unactivated 9400 System base component. Mix thoroughly and then add 1 gallon of 9401 Activator. 9404 may also be added to the 9400 System finishes after activation. Use 4 fluid ounces of 9404 per activated gallon of 9400 System finishes. The dry time of the 9400 finishes may be shortened by adding 9404 Leveling Additive.

Note: Do not use this product with Low VOC 9400 System finishes activated with HS9401 Activator

PHYSICAL PROPERTIES

Physical Properties		9404 LEVELING ADDITIVE
Composition		A blend of surfactants cut in ketones and aromatic hydrocarbons
Weight	Per Gallon	7.00 lbs.
	Per Liter	0.84 kg
Mixing Ratio		4 fluid ounces of 9404 Leveling Additive per gallon of activated 9400 system finish. (One 8 ounce container of 9404 per 2 gallons of activated finish).
Shelf Life		5 years
Safety Information		For additional information, see MSDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Phone: 877•385•8155 www.rustoleum.com/industrial Form: GDH-870 Rev.: 052715